

## 2004, pag. 129-138


## Preparation of rare-earth manganite-oxide thin films by metalorganic aerosol deposition technique

Moshnyaga V., Khoroshun I., Sidorenko A., Petrenko P., Weidinger A., Zeitler M., Rauschenbach B., Tidecks R., Samwer K.

https://doi.org/10.1007/s12034-013-0574-9

## Abstract

MgB2 thin films were fabricated on *r*-plane Al<sub>2</sub>O<sub>3</sub> (1102) substrates. First, deposition of boron was performed by rf magnetron sputtering on Al<sub>2</sub>O<sub>3</sub> substrates and followed by a post-deposition annealing at 850 °C in magnesium vapour. In order to investigate the effect of Fe<sub>2</sub>O<sub>3</sub> nanoparticles on the structural and magnetic properties of films, MgB<sub>2</sub> films were coated with different concentrations of Fe<sub>2</sub>O<sub>3</sub> nanoparticles by spin coating process. The magnetic field dependence of the critical current density  $J_c$  was calculated from the M–H loops and magnetic field dependence of the pinning force density,  $f_p(b)$ , was investigated for the films containing different concentrations of Fe<sub>2</sub>O<sub>3</sub> nanoparticles. The critical current densities, Jc, in 3T magnetic field at 5 K were found to be around 2•7 × 10<sup>4</sup> A/cm<sup>2</sup>, 4•3 × 10<sup>4</sup> A/cm<sup>2</sup>, 1•3 × 10<sup>5</sup> A/cm<sup>2</sup> and 5•2 × 10<sup>4</sup> A/cm<sup>2</sup> for films with concentrations of 0, 25, 50 and 100% Fe<sub>2</sub>O<sub>3</sub>, respectively. It was found that the films coated with Fe<sub>2</sub>O<sub>3</sub> nanoparticles have significantly enhanced the critical current density. It can be noted that especially the films coated by Fe<sub>2</sub>O<sub>3</sub> became stronger in the magnetic



2004, pag. 129-138

field and at higher temperatures. It was believed that coated films indicated the presence of artificial pinning centres created by  $Fe_2O_3$  nanoparticles. The results of AFM indicate that surface roughness of the films significantly decreased with increase in concentration of coating material.